



## Optional Application of Primer Surfacer

### Application



1. Check surface for cleanliness, apply 467-9 filler into low areas and sand to desired smoothness.
2. Then apply the Alumigrip® 10P30-8 surfacer with two coats being applied at 3 to 4 wet mils per coat and 30 minutes flash time in between coats.
3. Surfacer must be allowed to flash for at least 4 hours, depending on thickness of surfacer, before sanding can begin. The application of heat for force cure is not recommended.
4. Sand surface with 240 to 320 grit paper until desired smooth surface is achieved.
5. Blow dry the aircraft, check masking, tack surface, and apply topcoat.

### Safety Precautions

Comply with all local safety, disposal and transportation regulations. Check the Material Safety Data Sheet (MSDS) and label of the individual products carefully before using the products. The MSDSs are available on request.

#### Issue date: June 2010 (supersedes December 2009) - FOR PROFESSIONAL USE ONLY

**IMPORTANT NOTE** The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advice given is subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel.